



TEST REPORT

Page 1 of 5

REPORT NUMBER : TURR130134391

APPLICANT NAME ÇET-SAN Pls. Elk. Malz. San. Tic. Ltd.

ADDRESS İkitelli Org. San. Böl. İpkas San. Sit.
Fax : 5494812
Attention : Selahattin Ulaş (info@cet-san.com.tr)

SAMPLE DESCRIPTION : One sample of Orange plastic box

DATE IN : 11 September, 2013 (8:23)

DATE OUT : 25 September, 2013

PRODUCT'S CODE : See Attachement

TEST	Sample
HALOGEN CONTENT	NR

P = MEETS BUYER' S REQUIREMENT / F = DOES NOT MEET BUYER' S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES / X=NOT PERFORMED

The test results relate only to the items tested. The whole and/or the part of this test report shall not be reproduced and shall not be shared with third parties, nor to be used for PR activities without the written permission of INTERTEK Test Hizmetleri A.S.

PP

Zübeyde Altürk

Bora Şirinbilek
Coordinator

Neslihan Sözer
Chemical Laboratory Manager

Intertek Test Hizmetleri A.S.
Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY
Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55
e-mail : intertekcg.turkiye@intertek.com
www.intertek-turkey.com



130134391

PK.0562	Plastic Wedge 14 - 18
PK.0639	Snap-on Box
PK.0628	Snap-on Deep Box
PK.0637	Norm Box
PK.0638	Norm Junction
PK.0630	Plasterboard Box
PK.0632	Plasterboard Junction

(±) (I) HALOGEN CONTENT

Testing Item	Result (mg/kg)
Fluorine (F) Content	ND
Chlorine (Cl) Content	67
Bromine (Br) Content	ND
Iodine (I) Content	ND

Remarks : Ppm = Parts Per Million
ND = Not Detected


Test Method :

Testing Item	Testing Method	Reporting Limit
Halogen (F, Cl, Br, I) Content	With reference to BS EN 14582:2007 by Calorimetric Bomb and determined by Ion Chromatography	50 ppm

Remarks : Reporting Limit = Quantitation Limit of Analyte in sample

(±) This test was performed by Intertek Shenzhen

(‡) (II) MEASUREMENT FLOWCHART :
TEST FOR HALOGEN CONTENT
REFERENCE METHOD : BS EN 14582 : 2007



(‡) This test was performed by Intertek Shenzhen



END OF TEST REPORT